

Project Monofilaments/Textile Systems



CAPROWAX P™ 6006-00-000

compostable material according to DIN EN 13432 (layer thickness 500 µm)

Test material: CAPROWAX P®6006-00-000, proofed, by MFPA, the official material test establishment of the Bauhaus-University Weimar.

- for monofilaments and textile systems

A 6 to 7-fold stretching process reached strength of 130-140 N/mm².

Suitable as „no metallic binding wire“, strings, tracery, knotted and bound systems, thin ropes, webs and fabrics

CAPROWAX P™ compostable of course

