

CAPROWAX P™ 6070-T215 lumpy material

Applications: Thermoforming bioplastic modelling mass and joint sealer

Kunden Information:
Fon +49 (0)7625 918458
info@polyfea2.de
www.caprowax-p.eu

Testmaterial for
customer projects
Product information
09/2020

Albrecht Dinkelaker
Polymer- and product development
Blumenweg 2
D 79669 Zell im Wiesental

Physical Properties

Physical form		lumpy material <30 mm
Density at 23 °C	g/cc	1,05-1,15
Beginning of softening	°C (°F)	≈ 50 (122)

*) Based on the biological sources of waxes different values of viscosity could be occur

Tensile strength and elongation are dependent of temperature and stretching conditions

Measurements make only sense with comparable process conditions and thickness of moulded or stretched articles

Description

CAPROWAX P™ 70-T215 is a translucent/opaque polymer-/waxblend. Bioplastic modelling mass and joint sealer malleable at 65-40°C (149°-104°F)
All components are readily biodegradable

Advantages

consists of aliphatic, home/industrial compostable, certified polyester and modified, readily biodegradable, renewable, GMO-free plant oil.
≈ 90% of organic carbon are biobased
Waterproof, stable in use, cold-flexibel, solvent-free

No food or feeding stuff

GM-free, no content of starch or PLA

Ecofriendly composition

Without content of aromatic or nitrogenous substances

Applications

Thermoforming moulding, filler and levelling compound for moulding, support, embedding material, form and bandage
Mock-up and joint about 1 - 10 mm thickness
Suitable for compostable one-way-products,
preferably in agriculture or horticulture environment

Thermoforming

Heating in convection oven, hot plate or blow-dryer to 60-65 °C (140-149°F), then thermoforming and adapt by knead or filling at 65-40°C

! Attention please ! ! Security advice !

Use protective gloves !!! Such as thin leather gloves
Above 70°C (158 °F) melt becomes stickily and makes combustion !!!

Storage

Avoid heat and moisture, storage in original containers only

CAPROWAX P™ compostable of course