

Masterbatch CAPROWAX P™ Blue G 510 lw tex

Compostable carrier material: Bio-Dry-Blend CAPROWAX P 6006-C65 (Intermediate)

Customs-Tariff-No.: 3907 99 80

Customer information
Fon: +49 69 76 89 39 10
info@polyfea2.de
www.caprowax-p.eu

Product example

Albrecht Dinkelaker
Polymer- and Product Development
Talstrasse 83
D 60437 Frankfurt am Main

Properties / Data / Description			
Form	a)	mm	Pellets, Diameter: 1,5-3,0 / Size:2,0-3,5
Content of pigments	b)	%	25
Colour Index	PB 29		Ultramarine Blue
Colour Index	PW 6		Titandioxide
Colour description	c)		blue, greenish, covering
Lightfastness	d)		7-8
Bulk density	DIN EN ISO 60	g/l	754
Density	DIN EN ISO 1183	g/cm ³	1,21
Residual Humidity (LOD)	105°C/1h	%	< 0,3
Softening beginning	DSC	°C	57-63
Remark: tex = suited for colouration of filaments / heatstable up to 200-220°C / acid sensitive			
a) internal test norm b) Pigment determination proportionally c) 2% Masterbatch in CAPROWAX P 6006 lw = low content TiO ₂ d) Data of pigment producer Based on the biological sources different values of measurement could be occur			

Description CAPROWAX P™ Blue G 510 lw tex, a masterbatch with harmless, lightfast, non-migratory, temperature stable, insoluble in water, inorganic pigments partially comparable with natural pigments. Low-dusty incorporated in a compostable carrier material. Coloured bioplastics comply the specifications of DIN EN 13432

Carrier material CAPROWAX P 6006-C65: consists of aliphatic, home/industrial compostable, certified polyester and modified, readily biodegradable, renewable, GMO-free plant oil.

MFPA Test certificate: P31/029-05
*) calculated The carrier material is comparable with the test material CAPROWAX P® 6006 DIN EN 13432 tested by MFPA Weimar 83,7% of organic carbon are biobased *)

No food or feeding stuff eco-/compost friendly composition GM-free, no content of starch or PLA
Without content of aromatic or nitrogenous substances
Harmless, soil-similar, inorganic pigments

Biopolymers and use Covering colouration of bioplastics/biocomposites/blends as PLA, PBS, PHA, PCL, CAPROWAX P™/Blends, Bio-NFC/-WPC Polysaccharides/Derivates, Casein, PVAc/Bioplastic-Blends, PVOH, Bio-TPE, Bio-UPR, NIPU. For use as colouring additive suited for products of agriculture, garden and environment.

Introduction to recipe for reduced content of TiO₂ (lw) 1-2% Masterbatch (MB) homogenous intermixing with pellets yield in coloured products a content of ≤0,1% TiO₂
Processing temperatures 90-200°C (194-392°F) / short time up to 220°C (428°F)
Drying pellets on demand 50°C (122°F)/12h Avoid heating melt >90°C over long time

Examples of application Products of injection moulding, vacuum-/blowforming, foils, hotmelts, NF-BioComposites, support material, substrate, coating

Storage/Instruction Avoid heat and moisture, storage in original containers only

CAPROWAX P™ compostable of course

